



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

☞ JIS G 2308 : 1998

Ferrovanadium

ICS 77.100

Descriptors : ferrovanadium, ferro-alloys, vanadium-containing alloys

Reference number : JIS G 2308 : 1998 (E)

G 2308 :1998

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of International Trade and Industry through deliberations at Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law. Consequently **JIS G 2308 : 1986** is replaced with **JIS G 2308 : 1998**.

Date of Establishment: 1950-07-28

Date of Revision: 1998-02-20

Date of Public Notice in Official Gazette: 1998-02-20

Investigated by: Japanese Industrial Standards Committee

Divisional Council on Iron and Steel

JIS G 2308:1998, First English edition published in 1999-02

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

Ferrovandium

Introduction This revision is carried out for the purpose of compliance with the corresponding International Standard.

The Annex to this Standard is prepared based on ISO 5451, *Ferrovandium—Specification and conditions of delivery*, issued as the first edition in 1980 without changing the technical contents and can be applied in place of the provisions in the text of this Standard.

The " Informative reference" underlined with dotted line in this Annex is the item which does not exist in the original International Standard.

1 Scope This Japanese Industrial Standard specifies the ferrovandium to be used mainly as additive of alloy composition for manufacturing of iron and steel.

2 Normative references The following standards contain provisions which, through reference in this Standard, constitute provisions of this Standard. The most recent editions of the standards indicated below shall be applied.

JIS G 1301 *General rules for chemical analysis of ferroalloys*

JIS G 1318 *Method for chemical analysis of ferrovandium*

JIS G 1351 *Method for X-ray fluorescence spectrometric analysis of ferroalloys*

JIS G 1501 *General rules for sampling of ferroalloys*

JIS G 1602 *Methods of sampling for chemical analysis of ferroalloys (Part 2: Ferrotungsten, ferromolybdenum, ferrovandium, ferrotitanium and ferroniobium)*

JIS G 1641 *Methods of sampling for size analysis of ferroalloys and size determination*

3 Classification and symbol The class and symbol shall be as given in Table 1.

Table 1 Class and symbol

Class		Symbol
Ferrovanadium	No. 1	FV 1
	No. 2	FV 2

4 Method of lot formation

4.1 The lot formation shall be made by any one of the graded lot method, blended lot