



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

☞ JIS K 6781 : 1994

Polyethylene films for agriculture

ICS 83.140.10

Descriptors : polyethylene, films (states of matter), agricultural facilities, agricultural materials, polymers

Reference number : JIS K 6781 : 1994 (E)

K 6781 : 1994

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of International Trade and Industry through deliberations at Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law:

Date of Establishment: 1956-12-15

Date of Revision: 1994-07-01

Date of Public Notice in Official Gazette: 1994-07-12

Investigated by: Japanese Industrial Standards Committee
Divisional Council on High Molecular
Materials

JIS K 6781:1994, First English edition published in 2000-03

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

Polyethylene films for agriculture

1. Scope

This Japanese Industrial Standard specifies polyethylene films for agricultural uses, hereinafter referred to as the "film".

Remarks 1. Normative references to this Standard are as follows:

JIS B 7503-Dial Gauges

JIS Z 8401-Rules for Rounding off of Numerical Values

2. Units and numerical values given in { } in this Standard are based on the traditional units, and are appended for reference.

2. Classification

The films shall be classified into those manufactured by the inflation method, hereinafter referred to as the "I method", and those by the T-die method, hereinafter referred to as the "T method", which are further subdivided into five classes according to their thickness.

Class 1	0.1 mm
Class 2	0.07 mm
Class 3	0.05 mm
Class 4	0.03 mm
Class 5	0.02 mm