



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS R 5212 : 2009

(JCA)

Portland pozzolan cement

ICS 91.100.10

Reference number : JIS R 5212 : 2009 (E)

Date of Establishment: 1950-03-16

Date of Revision: 2009-11-20

Date of Public Notice in Official Gazette: 2009-11-20

Investigated by: Japanese Industrial Standards Committee
Standards Board
Technical Committee on Civil Engineering

JIS R 5212:2009, First English edition published in 2010-12

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

Contents

	Page
1 Scope	1
2 Normative references	1
3 Classification and composition	1
4 Quality	2
5 Constituents	2
5.1 Clinker	2
5.2 Portland cement	2
5.3 Siliceous admixture	2
5.4 Gypsum	3
5.5 Minor additional constituents	3
5.6 Grinding aids	3
6 Test method	3
6.1 Density, specific surface area, setting, soundness and compressive strength	3
6.2 Chemical composition	3
7 Inspection	3
8 Packaging	4
9 Package marking	4
10 Report	4
Annex A (informative) Comparison table between the present and previous editions of this Standard on technically significant revisions	8

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by Japan Cement Association (JCA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14. Consequently **JIS R 5212:1997** has been replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with a patent right, application for a patent after opening to the public, utility model right or application for registration of utility model after opening to the public which have technical properties. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying the patent right, application for a patent after opening to the public, utility model right or application for registration of utility model after opening to the public which have the said technical properties.

Portland pozzolan cement

1 Scope

This Japanese Industrial Standard specifies portland pozzolan cement.

Matters revised from the previous edition that are of technical significance are explained in Annex A in the form of a table of comparison between this edition and the previous edition.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS A 6201 *Fly ash for use in concrete*

JIS M 8850 *Methods for chemical analysis of limestone*

JIS R 5201 *Physical testing methods for cement*

JIS R 5202 *Methods for chemical analysis of cements*

JIS R 5204 *Chemical analysis method of cement by x-ray fluorescence*

JIS R 5210 *Portland cement*

JIS R 5211 *Portland blast-furnace slag cement*

JIS R 9151 *Gypsum for portland cement retarder*

JIS Z 1505 *Kraft paper sacks—For cement*

3 Classification and composition

The portland pozzolan cement shall be classified into three classes in table 1 according to the siliceous admixture content, and includes the cement composed of portland cement (see 5.2) and siliceous admixture (see 5.3) and the cement composed of clinker (see 5.1), gypsum (see 5.4), minor additional constituent¹⁾ (see 5.5) and siliceous admixtures (see 5.3).

In addition, in the case of the former composition, when siliceous admixture is contained in portland cement as the minor additional constituent specified in 5.3 of JIS R 5210, that amount shall be included in the siliceous admixture content in table 1. In the case of the latter composition, the amount of minor additional constituent (see 5.5) shall be not more than 5 %, in mass, of the total amount of clinker, gypsum and minor additional constituent. Furthermore, the amount of grinding aids used shall be less than 1 %, in mass, of the portland pozzolan cement.

Note ¹⁾ The minor additional constituent here does not include siliceous admixture.